




Brown 8
 CI Pigment Black 12
 Iron Titanium Brown
 Spinel

A medium brown powder produced by high temperature calcination. This pigment has fair UV and visible opacity, is chemically inert, heat resistant, and stable to ultraviolet light. It is non-bleeding and non-migratory. It has exceptional durability, and is generally used in applications where resistance to heat, light, and weather are needed. It is compatible with most resin systems and polymers, and is non-warping

[Product Information](#)

Reflectance



[Visible Only](#) [300-2500 nm](#)

Revision Date:	Apr-01-2002
Specific Gravity	4.3
Oil Absorption	14 kg/100 kg
Residue 325 mesh [44 µm]	0.07 wt%
Average Particle Size	1.2 µm
pH	8.5
Heat Stability	1000 °C
Conductivity	100 µS/cm
Percent Moisture	0.2 wt%
Lightfastness	8 (1-8)
Weatherability	5 (1-5)
Acid Resistance	5 (1-5)
Alkali Resistance	5 (1-5)
Bulk Density	0.61 kg/L